

AD-A043 374


NATIONAL BUREAU OF STANDARDS WASHINGTON DC POLYMERS DIV F/G 20/3  
PYROELECTRICITY AND CHARGE TRANSPORT IN A COPOLYMER OF VINYLIDE--ETC(U)  
JUL 77 M G BROADHURST, G T DAVIS, S C ROTH N00014-77-F-0007

UNCLASSIFIED

AD  
A043 374



END  
DATE  
FILMED  
9-77  
DDC



REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER <u>6</u>	2. GOVT ACCESSION NO. <u>JES</u>	3. RECIPIENT'S CATALOG NUMBER <u>9</u>
4. TITLE (and Subtitle) Pyroelectricity and Charge Transport in a Copolymer of Vinylidene Fluoride and Tetra- fluoroethylene		5. TYPE OF REPORT & PERIOD COVERED Technical Report
7. AUTHOR(s) M. G. Broadhurst, G. T. Davis, S. C. Roth and R. E. Collins		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS National Bureau of Standards Bulk Properties Section, Polymers Division Washington, D. C. 20234		8. CONTRACT OR GRANT NUMBER(s) N00014-77A0007 -F-
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Chemistry Program Office Arlington, Va. 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 356-522
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) <u>11 Jul 77</u>		12. REPORT DATE July 1, 1977
16. DISTRIBUTION STATEMENT (of this Report) According to the attached distribution list <u>12/17p.</u>		13. NUMBER OF PAGES 12
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		15. SECURITY CLASS. (of this report) Unclassified
18. SUPPLEMENTARY NOTES To be published in the Proceedings of the Conference on Electrical Insulation and Dielectric Phenomena		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Charge transport; piezoelectric; polarization; distribution; poling temperature; polyvinylidene fluoride copolymer; pyroelectric; thermal pulse		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A copolymer of 73 weight percent vinylidene fluoride and 27 weight percent tetrafluoroethylene can be made piezoelectric and pyroelectric by the temporary application of high electric fields. The application of a thermal pulse technique to the active films reveals that they are polarized preferentially near the posi- tive electrode and that the polarization extrudes further into the film as the poling temperature is increased. These observations can be made consistent with earlier data which show the piezoelectric and pyroelectric coefficient to be		

DDC  
RECEIVED  
AUG 25 1977  
C

AD A 043374

AD No.  
DDC FILE COPY

DD FORM 1473

EDITION OF 1 NOV 65 IS OBSOLETE  
S/N 0102-014-6001

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

410345

B

20.

independent of poling temperature by proposing charge transfer through the unpoled region of the polymer. Transient charge flow following a step-increase in temperature and pyroelectric response from layered structures support this explanation.

ACCESSION FOR	
RTM	WFO Section <input checked="" type="checkbox"/>
DDO	DW Section <input type="checkbox"/>
MANAGEMENT	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
DOW AVAILABLE/NOT AVAILABLE	
A	

12

OFFICE OF NAVAL RESEARCH

Contract N00014-77-F-0007

Task No. NR 356-522

Technical Report

PYROELECTRICITY AND CHARGE TRANSPORT IN A COPOLYMER  
OF VINYLIDENE FLUORIDE AND TETRAFLUOROETHYLENE

by

M.G. Broadhurst, G.T. Davis, S.C. Roth, and R.E. Collins

Prepared for Publication in the  
Proceedings of the Conference on Electrical  
Insulation and Dielectric Phenomena

National Bureau of Standards  
Bulk Properties Section  
Washington, D. C. 20234

July 1, 1977

Reproduction in whole or in part is permitted for any purpose  
of the United States Government.

Approved for Public Release; Distribution Unlimited

Pyroelectricity and Charge Transport in a Copolymer of Vinylidene Fluoride and Tetrafluoroethylene, M.G. Broadhurst, G.T. Davis and S.C. Roth, NBS, Washington, D.C., 20234, and R.E. Collins, AWA Research Laboratory, North Ryde, NSW, Australia.

## I. Introduction

Previous investigations have shown that a copolymer of vinylidene fluoride and tetrafluoroethylene can be made piezoelectric and pyroelectric by the temporary application of an electric field.<sup>\* 1,2</sup> For applied fields in excess of about 250 kV/cm, the electrical response became independent of applied field, independent of poling temperature between 0° and 60°C, and independent of poling time between 5 minutes and 7 hours.<sup>1,2</sup> Such behavior implied saturation of polarization and values of polarization required to account for the piezoelectric response were well within the maximum to be expected from alignment of dipoles within the crystalline phase of the copolymer. Measurements on similar films now indicate that the polarization distribution within the films is non-uniform and varies with poling temperature. This paper will present these results and will propose a model of charge transfer within the film to reconcile the evidence for saturation polarization and non-uniform charge distribution.

## II. Experimental

The copolymer used in this investigation was 73 weight percent vinylidene fluoride and 27 weight percent tetrafluoroethylene supplied to us as a powder by Pennwalt Corporation.<sup>3</sup> The powder was evacuated, compressed, and melted in a pellet-making mold commonly used for infrared sample preparation. Small pieces of the pellet were subsequently melted and pressed between Kapton<sup>3</sup> polyimide sheets from which the resultant copolymer films were easily removed. Such films were typically 30 to 50  $\mu$ m thick

---

\* Literature references have been kept to a minimum appropriate to an extended abstract.



and 3 cm in diameter. When quenched from the melt directly into ice water, the films were 35% crystalline based on density measurements. Aluminum or gold electrodes were evaporated onto both surfaces of the films. The electric field was applied across the sample thickness at room temperature heated to the desired temperature and returned to room temperature before the field was removed.

Since the copolymer crystallizes in a polar crystal form<sup>4</sup>, it can also be poled as it crystallizes from the melt. When crystallized in the presence of an applied field, two different techniques were used to minimize electrical breakdown. When the whole area of the sample was to be poled, a circular disc was cut from a 25  $\mu$ m thick polyimide sheet to be used as a spacer between brass electrodes. The copolymer pellet was then pressed into a film filling the void in the insulating Kapton spacer. When only a portion of the film was to be poled, gold electrodes and leads were evaporated onto Kapton sheets between which the copolymer was melted and pressed. The "sandwich" consisting of Kapton sheets and copolymer melt was transferred from the hot press into a copper sleeve immersed in a controlled temperature bath for poling and crystallization. After crystallization, graphite electrodes were painted on the surfaces for electrical measurements.

#### B. Measurements

The piezoelectric and pyroelectric response was measured as previously described<sup>5</sup>. Briefly, the short circuit current between the electrodes of the sample is measured as the temperature or pressure of the sample is slowly changed. The current per unit area divided by the rate of temperature or pressure change yields the desired coefficients. The pyroelectric response in some cases was also determined by measuring the total charge transferred following a rapid change in temperature. The sample was immersed directly into a stirred beaker of n-hexane and the temperature jump of one or two degrees was accomplished by adding small amounts of chilled or heated hexane.

An indication of the spatial distribution of polarization within the poled samples was obtained using a modification of the thermal pulsing technique reported by Collins<sup>6,7</sup>. The method relies upon the non-uniform temperature change in a thin film as a heat pulse diffuses through the thickness,  $d$ , of the film. Charge generated by the film,  $\Delta Q(t)$ , can be expressed as a function of the polarization distribution within the film,  $P(x)$ , and the temperature at any given plane  $\Delta T(x,t)$ . If the film is initially electrically neutral inside (as would occur for times after poling large compared with the electrical time constant  $\epsilon_0 \epsilon' \rho$ ), it can be shown<sup>7</sup> that

$$\Delta Q(t) = \frac{C \alpha_p}{\epsilon' \epsilon_0} \int_0^d P(x) \Delta T(x,t) dx \quad (1)$$

In the above expressions,  $\epsilon'$ ,  $\rho$  and  $C$  are the relative permittivity, resistivity and capacitance of the film respectively and  $\alpha_p$  is a temperature coefficient of permanent polarization. Evaluation of  $\alpha_p$  depends upon an understanding of the physical processes which lead to the change in polarization; a specific model has been presented elsewhere<sup>8</sup>.

### III. Results and Discussion

Figures 1 and 2 show results for two films poled at different temperatures. The charge generated was recorded as a function of time after the absorption of a short heat pulse. In Figures 1 and 2 curves a and b represent the charge generated when the heat pulse is incident on the side that was positive and negative respectively during poling. Curve c is a recording of the change in resistance of the aluminum electrode on the pulsed surface. It is representative of the change in temperature at that surface, and provides a measurement of the thermal time constant of the sample<sup>6</sup>.



It is evident that the charge pulses from the sample are quite different when it is heated from opposite sides, indicating spatial assymetry in the polarization within the film. A quantitative estimate of the spatial distribution of the polarization can be obtained by deconvoluting the data in Figures 1 and 2 using equation (1). The results are shown in Fig. 3. Only the broad features of the distribution are obtained by this technique; fine structure is not resolved.

In the sample poled at room temperature, the polarization is large only very close to that electrode which was positive during poling. Copolymer samples poled at 62, 71, 81, 92, 101 and 106°C also show polarization which is largest near this electrode, and which extends progressively further into the film as poling temperature is increased. Even at the highest poling temperature, however, the polarization is still highly non-uniform.

The spatial dependence of polarization presumably reflects, in some way, the spatial variation of electric field in the sample during poling. We have no convincing explanation of why the electric field in the polymer should be large near the positive electrode and, for lower poling temperatures, essentially zero through most of the polymer. The results suggest a contact dominated process. A possible model may be a reverse-biased p-n junction at the polymer-positive electrode interface with a depletion layer extending into the polymer.

The previous results<sup>1,2</sup> (pyroelectric coefficient essentially independent of poling temperature) and those of Fig. 3 (different fractions of the sample thickness poled) seemed initially to be conflicting. It can be demonstrated, however, that they are consistent with a model in which real charge migrates through the essentially unpoled region of the sample after a temperature change. This charge moves in the internal electric field produced by the temperature induced change in polarization. Charge motion continues until the internal electric field is zero.

Such a model predicts several features of this transient current. Firstly, the charge motion will take place at a rate dependent on the electrical time constant,  $\epsilon_0 \epsilon' \rho$  of the polymer. For PVF<sub>2</sub>-TFE copolymer, the resistivity  $\rho$  is time dependent, but measurements a few minutes after application of a voltage yield values around  $4 \times 10^{13}$  ohm cm at room temperature. The relative permittivity  $\epsilon'$ , is frequency dependent and, at 22°C, varies from 9.0 at 100 Hz to 14.2 at 0.01 Hz. The time constant corresponding to these values is about one minute.

This model also predicts the magnitude of the charge transfer for a sample in which the polarization decreases monotonically from one electrode (such as in the present case). The total charge generated (true pyroelectric charge plus the subsequent real charge motion) is proportional to the maximum value of polarization. It does not depend on how far that polarization extends into the sample or on the detailed spatial distribution. In the remainder of this paper evidence is presented which supports this interpretation of the above experimental results.

In order to obtain a more direct indication of the effect, the temperature of some samples was increased in a step-wise manner and the charge transferred was measured as a function of time. The experimental procedure was described above. Results for three different samples are shown in Fig. 4. Co-polymer films poled between 0° and 80°C show a rapid charge flow followed by a time-dependent current of which Fig. 4a is typical. The dotted line in Fig. 4a is an exponential curve with time constant of 0.78 minutes. This is of the order of the electrical time constant discussed above. On the other hand, co-polymer films crystallized in the presence of an electric field, and the homopolymer film, only show the initial rapid response (Fig. 4 b,c). Close examination of the data from the thermal pulsing experiment shows that the charge delivered is still increasing slightly when the temperature in the sample is uniform (Figs. 1, 2). This is also an indication of the beginning of the slow response of Fig. 4a.

To confirm that a non-uniformly poled sample could give just such a response, the pyroelectric response from a layered structure of unpoled copolymer and poled  $\text{PVF}_2$  was compared with that from poled  $\text{PVF}_2$  alone.  $\text{PVF}_2$  homopolymer capacitor grade material supplied by Kureha Chemical Corp.<sup>3</sup> was poled at 800 kV/cm for 30 minutes at 110°C. The pyroelectric response is indicated by the solid line in Fig. 5. It can be seen that the pyroelectric current accurately follows the rate of change of temperature. Immediately after obtaining this result, an unpoled copolymer film with electrodes on both sides was inserted between the  $\text{PVF}_2$  and the upper contact. The temperature was then changed as before. The results are indicated by the dashed line in Fig. 5. It can be seen that the current response due to a temperature change is not as rapid.

The apparent pyroelectric coefficient for these two cases is shown in Fig. 6 for different times after the commencement of a temperature change. The total charge transferred, obtained by integrating the data of Fig. 5, is found to be similar in both cases yielding a pyroelectric coefficient of  $2.45 \text{ nC/cm}^2 \text{ K}$  as indicated by the bar at the right of Fig. 6. It can be concluded that, under the nearly static measuring conditions here, a non-uniformly poled sample can yield the same pyroelectric response as a uniformly poled sample, if there is sufficient conductivity in the unpoled part of the polymer.

#### IV. Acknowledgement

Partial support of this work by the Office of Naval Research is gratefully acknowledged.

### Figure Captions

- Figure 1: Charge transfer between electroded surfaces of copolymer film poled at 23°C as a function of time following absorption of a heat impulse on one surface of the film; (a) when pulsed on the electrode which was positive during poling; (b) heat pulse on negative electrode; (c) resistance change of aluminum electrode which indicates temperature history of pulsed surface. Copolymer film is 44  $\mu\text{m}$  in thickness and was poled at 272 kV/cm for 20 minutes at room temperature. The heat pulse was 20  $\mu\text{s}$  long (FWHM) for the charge measurements and 50  $\mu\text{s}$  long (FWHM) for the resistance trace.
- Figure 2: Charge transfer between electroded surfaces of copolymer film poled at 101°C as a function of time following a heat impulse on one surface of the film; (a), (b) and (c) as in Fig. 1. Poling conditions were 255 kV/cm at 101°C for five minutes. Copolymer film is 47  $\mu\text{m}$  thick.
- Figure 3: Spatial distribution of polarization in copolymer films from (a) poled at 101°C, (b) poled at 23°C as in Figs. 1 and 2. The polarization is largest at the electrode that was positive during poling.
- Figure 4: Charge transfer between opposing surfaces of polymer film as a function of time following a step-wise change in temperature; (a) copolymer film poled at 0° in a field of 800 kV/cm; (b) copolymer film crystallized in presence of a field of 70 kV/cm; (c) poly(vinylidene fluoride) homopolymer poled for 30 minutes at 110° and 800 kV/cm. Pens for charge and temperature are physically offset.
- Figure 5: Pyroelectric current response and temperature as a function of time. Solid lines refer to a single film of poly(vinylidene fluoride) poled for 30 minutes at 110° and 800 kV/cm. Broken lines refer to same sample but with a film of unpoled copolymer between the active film and the top contact. Offset of pens in original data has been compensated in this tracing.



Figure 6: The apparent pyroelectric coefficient at various points in time from the curve in Fig. 5. Solid circles refer to the single film of homopolymer; open circles refer to the two-layer configuration. The bar at the right corresponds to the coefficient obtained from integration of either curve in Fig. 5. Time axis refers to point of departure of current from zero in Fig. 5.

#### References

1. G. T. Davis and M. G. Broadhurst, Anais de Academia Brasileira de Ciencias (to be published).
2. G. T. Davis and M. G. Broadhurst, "Piezoelectricity and Pyroelectricity in a Polyvinylidene fluoride Copolymer", NAS Conference on Electrical Insulation and Dielectric Phenomena, NBS, November 1975.
3. Commercial materials are identified in this paper to specify adequately the experimental procedure. Such identification does not imply recommendation or endorsement by the National Bureau of Standards
4. J. B. Lando and W. W. Doll, J. Macromol. Sci. - Phys. B2, 205-218 (1968).
5. M. G. Broadhurst, C. G. Malmberg, F. I. Mopsik, and W. P. Harris, Electrets, Charge Storage and Transport in Dielectrics, M. M. Perlman, ed., The Electro-Chemical Soc., Princeton, N.J. (1973) p. 492.
6. R. E. Collins, Rev. Sci. Inst., 48, 83 (1977).
7. R. E. Collins, J. Appl. Phys. 47, 4804 (1976).
8. F. I. Mopsik and M. G. Broadhurst, J. Appl. Phys., 46, 4204 (1975).






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5






FIG. 6

# TECHNICAL REPORT DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Stephen H. Carr Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Dr. D. R. Uhlman Department of Metallurgy and Material Science Center for Materials Science and Engineering Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1
Dr. M. Broadhurst Bulk Properties Section National Bureau of Standards U.S. Department of Commerce Washington, D.C. 20234	2	Naval Surface Weapons Center White Oak Silver Spring, Maryland 20910 Attn: Dr. J. M. Augl Dr. B. Hartmann	1
Dr. C. H. Wang Department of Chemistry University of Utah Salt Lake City, Utah 84112	1	Dr. G. Goodman Globe Union Inc. 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. T. A. Litovitz Department of Physics Catholic University of America Washington, D.C. 20017	1	Picatinny Arsenal SMUPA-FR-M-D Dover, New Jersey 07801 Attn: A. M. Anzalone Bldg. 3401	1
Dr. R. V. Submaranian Washington State University Department of Materials Science Pullman, Washington 99103	1	Dr. J. K. Gillham Princeton University Department of Chemistry Princeton, New Jersey 08540	1
Dr. M. Shen Department of Chemical Engineering University of California Berkeley, California 94720	1	Douglas Aircraft Co. 3855 Lakewood Boulevard Long Beach, California 90846 Attn: Technical Library Cl 290/36-84 AUTO-Sutton	1
Dr. R. S. Porter Polymer Research Institute and Polymer Science and Engineering University of Massachusetts Amherst, Massachusetts 01002	1	Dr. E. Baer Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. Morton Litt Dept. of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1	Dr. K. D. Pae Department of Mechanics and Materials Science Rutgers University New Brunswick, New Jersey 08903	1
Dr. V. Stannett Department of Chemical Engineering North Carolina State University Raleigh, North Carolina 27607	1		

# TECHNICAL REPORT DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Arlington, Virginia 22217 Attn: Code 472	2	Defense Documentation Center Building 5, Cameron Station Alexandria, Virginia 22314	12
Office of Naval Research Arlington, Virginia 22217 Attn: Code 102IP	6	U.S. Army Research Office P.O. Box 12211 Research Triangle Park, North Carolina 27709 Attn: CRD-AA-IP	
ONR Branch Office 536 S. Clark Street Chicago, Illinois 60605 Attn: Dr. George Sandoz	1	Commander Naval Undersea Research & Development Center San Diego, California 92132 Attn: Technical Library, Code 133	1
ONR Branch Office 715 Broadway New York, New York 10003 Attn: Scientific Dept.	1	Naval Weapons Center China Lake, California 93555 Attn: Head, Chemistry Division	1
ONR Branch Office 1030 East Green Street Pasadena, California 91106 Attn: Dr. R. J. Marcus	1	Naval Civil Engineering Laboratory Port Hueneme, California 93041 Attn: Mr. W. S. Haynes	1
ONR Branch Office 760 Market Street, Rm. 447 San Francisco, California 94102 Attn: Dr. P. A. Miller	1	Professor O. Heinz Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	
ONR Branch Office 495 Summer Street Boston, Massachusetts 02210 Attn: Dr. L. H. Peebles	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
Director, Naval Research Laboratory Washington, D.C. 20390 Attn: Library, Code 2029 (ONRL)	6		
Technical Info. Div.	1		
Code 6100, 6170	1		
The Asst. Secretary of the Navy (R&D) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1		
Commander, Naval Air Systems Command Department of the Navy Washington, D.C. 20360 Attn: Code 310C (H. Rosenwasser)	1		

<u>No. Copies</u>	<u>No. Copies</u>
NASA-Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135 Attn: Dr. T. T. Serofini, MS-49-1 1	Dr. David Roylance Department of Materials Science and Engineerin Massachusetts Institute of Technology Cambridge, Massachusetts 02039 1
Dr. Charles H. Sherman, Code TD 121 Naval Underwater Systems Center New London, Connecticut 1	Dr. W. A. Spitzig United States Steel Corporation Research Laboratory Monroeville, Pennsylvania 15146 1
Dr. William Risen Department of Chemistry Brown University Providence, Rhode Island 02912 1	Dr. T. P. Conlon, Jr., Code 3622 Sandia Laboratories Sandia Corporation Albuquerque, New Mexico 87115 1
Dr. Alan Gent Department of Physics University of Akron Akron, Ohio 44304 1	Dr. Martin Kaufmann, Head Materials Research Branch, Code 4542 Naval Weapons Center China Lake, California 93555 1
Mr. Robert W. Jones Advanced Projects Manager Hughes Aircraft Company Mail Station D 132 Culver City, California 90230 1	Dr. Charles Hicks Naval Undersea Center San Diego, California 92132 1
Dr. C. Giori IIT Research Institute 10 West 35 Street Chicago, Illinois 60616 1	Mr. A. Johnson N43-12 National Highway Traffic Safety Admin. 1 2100 2nd Street, S.W. Washington, D.C. 20590
Dr. Jerome B. Lando 1 Dept. of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	